

Doc nummer: 202102028 Report date: 15/07/2021

Fabric reference: Genial 810025 Date analyses: 28/06/2021 - 15/07/2021

Place analyses: Labotex

Customer: BM Fabrics Date of request: 28/06/2021

Hoogstraat 177 B Samples received: 29/06/2021

9550 Herzele

Testing and conditioning in standard atmosphere, T (20+/-2)°C and RH (65+/-4)%

Specification	Results	Remarks	!
M1-test			
NF P92-503	M1 M1		
NF P92-504	M2		
NF P92-505	M3		
W 132 303	M4		!
BE	(more details: see annex and classification scheme)		
364-TEST			

Labotex certifies that the results mentioned in this report are obtained after testing in accordance with the procedure and equipment specified by the concerned standards, unless noted differently.



Joeri Neys - Laboratory Manager

Labotex has the competence to perform tests in accordance with the requirements of standard NBN EN ISO/IEC 17025. The scope of this accreditation can be obtained on request.

The results in this report only relate to the tested items.

Samples will be returned to the customer with the certificate, if possible. Samples will not be retained, unless specified by the customer. Retained samples will be kept for maximum one year unless a specific retention period is necessary.

 $This \ report\ can \ not\ be\ copied\ unless\ in\ its\ complete\ form\ and\ with\ written\ approval\ of\ Labotex\ (Kontich).$

Sampling is performed by the costumer. Fabric analysed as received. $\label{eq:costumer}$

Uncertainty of measurement on the test result is not taken into account when assessing compliance with the specifications.

The uncertainty and the description of the methods are available at the lab on request.

ANA00022 Page 1 of 4 Approval date: 02/10/2020



Doc nummer: 202102028 Report date: 15/07/2021

Fabric reference: Genial 810025 Date analyses: 28/06/2021 - 15/07/2021

Place analyses:

Labotex

Customer: BM Fabrics Date of request: 28/06/2021

Hoogstraat 177 B Samples received: 29/06/2021

9550 Herzele

Testing and conditioning in standard atmosphere, T (20+/-2) $^{\circ}$ C and RH (65+/-4)%

Results of NF P92-503 to 505

		sample 1	sample 2	sample 3	sample 4
	side	face	reverse	face	reverse
	direction	warp	warp	weft	weft
NF P92-503	handling period (min)	5	5	5	5
	hole formation	yes	yes	yes	yes
	afterflame / afterglow time (s)				
	cycle 1	0.0	0.0	0.0	0.0
	cycle 2	0.0	0.0	0.0	0.0
	cycle 3	0.0	0.0	0.0	0.0
	cycle 4	0.0	0.0	0.0	0.0
	cycle 5	0.0	0.0	0.0	0.0
	cycle 6	0.0	0.0	0.0	0.0
	cycle 7	0.0	0.0	0.0	0.0
	cycle 8	0.0	0.0	0.0	0.0
	cycle 9	0.0	0.0	0.0	0.0
	cycle 10	0.0	0.0	0.0	0.0
	damaged length (mm)	75	105	105	120
	damaged width (mm)	55	55	60	92
	burning molten droplets	no	no	no	no
	not burning molten droplets	yes	yes	yes	yes
	burning debris	no	no	no	no
	not burning debris	yes	yes	yes	yes

ANA00022 Page 2 of 4 Approval date: 02/10/2020

Version: 19.0



Doc nummer: 202102028 Report date: 15/07/2021

Fabric reference: Genial 810025 Date analyses: 28/06/2021 - 15/07/2021

Place analyses:

Labotex

Customer: BM Fabrics Date of request: 28/06/2021

Hoogstraat 177 B Samples received: 29/06/2021

9550 Herzele

Testing and conditioning in standard atmosphere, T (20+/-2) $^{\circ}$ C and RH (65+/-4)%

NF P92-504 droplets afterflame time (s)

not burning	not burning	not burning	not burning
0.0	0.0	0.0	0.0
0.0	0.0	0.0	0.0
0.0	0.0	0.0	0.0
0.0	0.0	0.0	0.0
0.0	0.0	0.0	0.0
0.0	0.0	0.0	0.0
0.0	0.0	0.0	0.0
0.0	0.0	0.0	0.0
0.0	0.0	0.0	0.0
0.0	0.0	0.0	0.0
0.0	0.0	0.0	0.0
0.0	0.0	0.0	0.0
0.0	0.0	0.0	0.0
0.0	0.0	0.0	0.0
0.0	0.0	0.0	0.0
0.0	0.0	0.0	0.0
0.0	0.0	0.0	0.0
0.0	0.0	0.0	0.0
0.0	0.0	0.0	0.0
0.0	0.0	0.0	0.0

sample 1 sample 2 sample 3 sample 4

unation 140

0

0

no

direction

side

ignition of the cellulose ignition of the sample after flaming time of the sample

burning droplets

face	reverse	face	reverse
warp	warp	weft	weft
no	no	no	no

0

0

0

0

0

no

ANA00022 Page 3 of 4 Approval date: 02/10/2020

Version: 19.0

NF P92-505



Doc nummer: 202102028 Report date: 15/07/2021

Fabric reference: Genial 810025 Date analyses: 28/06/2021 - 15/07/2021

Place analyses: Labotex

Customer: BM Fabrics Date of request: 28/06/2021

Hoogstraat 177 B Samples received: 29/06/2021

9550 Herzele

Testing and conditioning in standard atmosphere, T (20+/-2)°C and RH (65+/-4)%

Classification scheme

Criteria for M1 classification

NF P92-503

- * afterflame time ≤5s
- * damaged length ≤ 250mm
 - * no burning droplets

NF P92-504

- * afterflame time ≤ 2s
- * no burning droplets

NF P92-505

- * no ignition of the cellulose
 - * no burning droplets

Criteria for M2 classification

NF P92-503

- * afterflame time > 5s
- * damaged length ≤350mm
 - * no burning droplets

NF P92-504

- * afterflame time ≤5s
- * no burning droplets

NF P92-505

- * no ignition of the cellulose
 - * no burning droplets

Criteria for M3 classification

NF P92-503

- * afterflame time > 5s
- * damaged length \geq 350mm and < 600mm
- * damaged width ≤ 90mm at the length between 450 mm and 600mm
 - * no burning droplets

NF P92-504

- * afterflame time > 5s
- * no burning droplets

NF P92-505

- * no ignition of the cellulose
 - * no burning droplets

Criteria for M4 classification

If the fabric doesn't meet with the criteria for a M1, M2 or M3 classification, it is classified M4.

ANA00022 Page 4 of 4 Approval date: 02/10/2020