

BM Fabrics Hoogstraat 177 B9550 Herzele

Your notice of 11-12-2023

Your reference 61769 + 61802

Date 27-06-2024

Analysis Report 23.06623.10

Modification

Required tests :

EN 13773 (2003)

Sample id	Updated information given by the client	Date of receipt
T2327909	820022 GUAVA	11-12-2023

gréelle

Gina Créelle Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel. The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.





CENTEXBEL • textile competence centre • www.centexbel.be • www.vkc.be

GENT • Technologiepark 70 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 29 27 00 • fax +32 56 29 27 01 • info@vkc.be VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB



Analysis Report 23.06623.10 Date 27-06-2024 Page 2/6

Samples

T2327909 820022 GUAVA



in

f



Reference: T2327909 - 820022 GUAVA

<u>Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the</u> <u>ignitability of vertically oriented specimens.</u>

Date of ending the test Standard used Product standard 23-01-2024 EN 1101 (1995) + A1 (2005) EN 13773 (2003)

20°C, relative humidity 65%

19°C, relative humidity 38%

Deviation from the standard

Conditioning Testing atmosphere

Ignition

Bottom edge

-

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.



Length		
Flame application	Cases of	Cases of
time (s)	ignition	non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
6	0	2
7	1	1
8	0	1
9	0	1
10	0	1
11	0	1
12	0	1
13	0	1
14	0	1
15	0	1
16	0	1
17	0	1
18	0	1
19	0	2
20	1	5

The mean of the recorded times at which ignition was observed is calculated The test requires at least five instances of ignition and five instances of non-ignition. Because less than 5 instances of ignition have been measured, and taking into account §12 of ISO 6940, a 'non-ignition' for this test is recorded

in

f



Width		
Flame application	Cases of	Cases of
time (s)	ignition	non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated No ignition within 20 s

in f



Reference: T2327909 - 820022 GUAVA

<u>Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of</u> <u>flame spread of vertically oriented specimens with large ignition source.</u>

Date of ending the test	23-01-2024
Standard used	EN 13772 (2011)
Product standard	EN 13773 (2003)

Deviation from the standard

Conditioning

20°C, relative humidity 65%

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length

	Front	Back	Back	Back
Severance1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	125	130	130	130
Flaming debris	no	no	no	no

Width

	Front	Back	Front	Front
Severance1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	130	130	135	135
Flaming debris	no	no	no	no

Classification in accordance with EN 13773

Class 1